

Product	Chem. Description	Features and Benefits
<b>NA-SUL 707</b>	Lithium Dinonylnaphthalenesulfonate (0.76%)	Low ash rust inhibitor with good high temperature stability in industrial oils and greases. Retards bleeding in lithium soap greases.
<b>NA-SUL 729</b>	Calcium Dinonylnaphthalenesulfonate (2.1%)	Outstanding demulsification properties, excellent filterability (dry and wet), thermal and hydrolytic stability. Highly effective dispersant for solid additives.
<b>NA-SUL 729-NF</b>	Calcium Dinonylnaphthalenesulfonate (1.9%) with Yellow Metal Deactivator (YMD)	Premium ferrous rust inhibitor plus yellow metal deactivator for non-ferrous corrosion protection. Synergistic with other additives, excellent solubility in a wide range of base stocks.
<b>NA-SUL BSN</b>	Barium Dinonylnaphthalenesulfonate (6.6%)	Non-staining rust inhibitor with outstanding demulsibility at all additive levels. Excellent thermal stability and compatibility with other additives. Outstanding synergy with other antirust additives.
<b>NA-SUL MG</b>	Magnesium Dinonylnaphthalenesulfonate (1.3%)	Low ash rust inhibitor with excellent filterability and hydrolytic stability. Synergy with other antirust additives. Promotes the formation of highly water-resistant films.
<b>NA-SUL SS</b>	Sodium Dinonylnaphthalenesulfonate (2.4%)	Forms a highly polar, hydrophobic film which is strongly bonded to metal surfaces. Solubility characteristics allow use in oil or water systems. Does not emulsify or demulsify.
<b>NA-SUL ZS</b>	Zinc Dinonylnaphthalenesulfonate (2.8%)	Excellent demulsibility, thermal and hydrolytic stability. Good filterability (dry and wet). Synergistic with ZnDTPs and antioxidants.