

Product	Bound Styrene (%)	Vinyl (%)	Viscosity (ML 1+4 at 100°C)	Extender Oil
SOL 5220 M	26,5	26	54	
SOL 5250 H	20	55,5	74	
SOL 5270 M	21	63	50	
SOL 5270 H	21	63	65	
SOL 5260 H	28	55	75	
SOL 5251 H	21	55	77	
SOL 5271 H	21	63	67	
SOL 1205	25 (20*1)	10	50	
SOL 6270 M	25	63	47	37,5 - TDAE
SOL 6270 SL	25	63	47	37,5 - TDAE
SOL C6270 L	25	63	63	37,5 - TDAE
SOL 6360 SL	34	48	47	37,5 - TDAE
SOL C6450 SL	35,5	40	53	37,5 - TDAE
SOL 6440 H	35,5	40	80	37,5 - TDAE
SOL 6361 H	34	58	70*2	37,5 - TDAE