

Product	Cristallization rate	Viscosity (ML 1+4 at 100°C)	Applications / properties
DENKA M-30	Medium	38 ± 4	General purposes, compounds with low viscosity
DENKA M-40 (new M 42)	Medium	48 ± 5	General purposes
DENKA M-41	Medium	48 ± 5	As M-40 but with less roll sticking and mold staining
DENKA M-70	Medium	70 ± 10	General purposes
DENKA M-100	Medium	100 ± 10	Industrial goods
DENKA M-120	Medium	120 ± 10	Sheets, hoses...
DENKA M 130 H	Medium	1510-2700 (c)	Industrial goods
DENKA S 40 V	Very slow	48 ± 5	Industrial goods with resistance to low temperatures
DENKA ES-40	Very slow	43 ± 4	Calendered sheets, extruded goods
DENKA ES-70	Very slow	75 ± 5	Similar to ES- 40, with high viscosity
DENKA EM-40	Medium	48 ± 5	Extruded goods with precise shapes
DENKA MT-40	Medium	48 ± 5	Calendered sheets, extruded goods
DENKA MT-100	Medium	95 ± 10	Extruded
DENKA PS-40 A	Slow	35 - 55	Belts, sponges..improved storage stability and low temperature resistance
DENKA DCR-30	Slow	65 ± 7	Industrial goods with low temperature resistance
DENKA DCR-40	Slow	40 - 55	Belts , sponges and molded goods
DENKA DCR-42A	Medium	40 - 55	Cables