

<b>Grade</b>	<b>Styrene [%]</b>	<b>Diblock content</b>	<b>Solution viscosity at 25°C, 25wt% Toluene</b>
SIS LH-11	15 wt%	>1 wt%	850-2000
SIS LH-70	15 wt%	60 wt%	400-1000
SIS LH-12	15 wt%	25 wt%	500-1500
SIS LH-13	30 wt%	< 1 wt%	200-700
SIS LH-50	15 wt%	50 wt%	500-1500