

<b>Grade</b>	<b>Softening Point °C (ASTM E28)</b>	<b>Color G# (ASTM D1544)</b>	<b>Acid V. (ASTM D974)</b>	<b>Application</b>
C9 GL100	95-105	3-5#	Max 0.1	HMA
C9 GL120	110-120	3-5#	Max 0.1	HMA
C9 GL130	120-130	3-5#	Max 0.1	HMA
C9 GP100	95-105	5-7#	Max 0.1	Wood HMA, Paints, Waterproof Adhesive
C9 GP120	110-120	5-7#	Max 0.1	Wood HMA, Paints, Waterproof Adhesive
C9 GP130	120-130	5-7#	Max 0.1	Wood HMA, Paints, Waterproof Adhesive
C9 GP140	130-140	5-7#	Max 0.1	Wood HMA, Paints, Waterproof Adhesive
C9 GP150	140-150	5-7#	Max 0.1	Wood HMA, Paints, Waterproof Adhesive