

Grado	Punto fusione °C (ASTM E28)	Colore G# (ASTM D1544)	Acidità (ASTM D974)	Applicazione
C9 GL100	95-105	3-5#	Max 0.1	HMA
C9 GL120	110-120	3-5#	Max 0.1	HMA
C9 GL130	120-130	3-5#	Max 0.1	HMA
C9 GP100	95-105	5-7#	Max 0.1	Legno HMA, vernici, membrane adesive
C9 GP120	110-120	5-7#	Max 0.1	Legno HMA, vernici, membrane adesive
C9 GP130	120-130	5-7#	Max 0.1	Legno HMA, vernici, membrane adesive
C9 GP140	130-140	5-7#	Max 0.1	Legno HMA, vernici, membrane adesive
C9 GP150	140-150	5-7#	Max 0.1	Legno HMA, vernici, membrane adesive